




DOP DIN PLUTA AGLOMERAT



DOP CILINDRIC MICROGRANULAT

TOLERANTA

DIMENSIUNI: D = 44/24; H = 42/27.5 mm



| | |
|-------------------------------|--|
| Inaltime : | ± 0.3 mm |
| Diametru : | ± 0.2 mm |
| Tesitura : | la cerere |
| Umiditate: | 4% - 8 % |
| Densitate: | 280kg/m ³ $\pm 6\%$ |
| Fora de extragere: | 15-40 daN |
| Porozitate : | < 1/3 din inaltime |
| Capacitatea de revenire : | dupa 5 min ≥ 90 % dupa 1 ora ≤ 92 % |
| Etansare: | 100% < 6 bar |
| Continut de praf/ dop : | ≤ 0.001 g/dop |
| Bacterii aerobe : | < 30 U.F.C./ dop |
| Ciuperci si drozii : | < 10 U.F.C./ dop |
| 2.4.6 TCA Tricloranisol : | ≤ 1.2 ng/l |
| PCA, TeCA, TBA: | sub limite cuantificabile |
| Examen olfactiv si gustativ : | absent |

Teste realizate dupa normele UNE 56922, UNE 56930.

