




DOP DIN PLUTA NATURALA



DOP CILINDRIC NATURAL

TOLERANTA

DIMENSIUNI : D = 24/26; H = 44/49 mm



Inaltime :	± 0.5 mm
Diametru :	± 0.4 mm
Tesitura :	4 mm ± 0.5
Umiditate :	4 % - 8%
Densitate :	125 – 230 kg/m ³
Porozitate :	≤ 2.5 mm
Capacitatea de revenire :	dupa 5 min ≥ 93 % dupa 1 ora ≤ 95 %
Forta de extragere:	20 - 40 daN
Continut de praf/ dop :	≤ 0.001 g/dop
Bacterii aerobe :	< 30 U.F.C./ dop
Ciuperci si drojdii :	< 10 U.F.C./ dop
2.4.6 TCA Tricloranisol :	< 2 ng/l < 2 ng/l
Examen olfactiv si gustativ :	absent

Teste realizate dupa normele UNE 56921.

